

LAMTEC[®]

Corporation

Metal Buildings
Duct Wrap
Duct Board
Pipe
Wood Roof Assemblies

[Home](#) | [About Us](#) | [Directio](#)

[Vapor Retarder](#) | [Product Selection Guide](#) | [Product Specs](#) | [Architectural Spe](#)



Building

Duct Wrap

Duct Board

Product Specifications

WMP-50

POLYPROPYLENE / SCRIM / CORE / METALLIZED POLYESTER

Meets ASTM C1136, Type I, II, III, IV

Contents: [\[Facing Composition\]](#) [\[Physical Properties\]](#) [\[Fire Testing\]](#)
([click for PDF format](#))

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
White Film	Polypropylene	0.0015 inch	38.1 micrometers
Adhesive	Flame Resistant		
Reinforcing	Tri-directional Fiberglass/Polyester	5 / inch (MD) 5 / inch (XD)	20 / 100 mm 20 / 100 mm
Core	Proprietary	30 lbs / 3000 ft ²	49 gm / m ²
Adhesive	Polymeric		
Film	Metallized Polyester	0.0005 inch	12.7 micrometers

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	32 lbs / 1000 ft ²	156 gm / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hr-ft ² -in Hg)	1.15 ng / m ² -s
Bursting Strength	ASTM D774	120 psi	8.4 kg / cm ²
Puncture Resistance	ASTM C1136	125 beach units	3.7 Joules
Tensile Strength	ASTM C1136	65 lbs/inch width (MD) 60 lbs/inch width (XD)	11.4 kn / m 10.5 kn / m
Caliper / Thickness	Micrometer	0.010 inch	254 micrometers
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination

High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains F No Delam
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delam
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Light Reflectance	ASTN C523	85%	85%

FIRE TESTING	UL 723 / ASTM E84		CAN ULC-S102M		BRITISH ST
	Flame Spread	Smoke Developed	Flame Spread	Smoke Developed	Parts / Summa
Polypropylene Exposed	5	30	5	30	Class 0
Polyester Exposed	5	20	5	20	

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

Copyright © 2006 [LAMTEC]

Outlook Web Ac