



1 PRODUCT NAME

STYROFOAM™ CAVITYMATE™ SC Insulation

2 Manufacturer

The Dow Chemical Company
Building & Construction
200 Larkin
Midland, MI 48674
1-866-583-BLUE (2583)
Fax 1-989-832-1465
www.dowstyrofoam.com
/architect

Dow Chemical Canada Inc.
Building & Construction
Suite 2200 250 - 6th Ave. SW
Calgary, AB T2P 3H7
English: 1-866-583-BLUE (2583)
French: 1-800-363-6210
www.dowstyrofoam.ca
/4architects

3 Product Description

BASIC USE

STYROFOAM™ CAVITYMATE™ SC extruded polystyrene insulation is an extruded polystyrene foam rigid board insulation with shiplap edges. It is designed for use as an exterior sheathing on steel stud walls in new commercial and residential high-rise buildings. It is also ideally suited for thermally upgrading existing structures.

SIZES

Thickness: 1", 1.5", 2" and 2.5"
Length: 96" Nominal
Width: 24" (Canada) or 48" (U.S./Canada) Nominal

4 Technical Data

APPLICABLE STANDARDS
ASTM International

- ASTM C518 – Standard Test

- Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- ASTM D1621 – Standard Test Method for Compressive Properties of Rigid Cellular Plastics
- ASTM C272 – Standard Test Method for Water Absorption of Core Materials for Structural Sandwich Constructions
- ASTM E96 – Standard Test Methods for Water Vapor Transmission of Materials
- ASTM D696 – Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics
- ASTM C578, Type X –

Standard Specification for Rigid, Cellular Polystyrene Insulation

- ASTM D2842 – Standard Test Method for Water Absorption of Rigid Cellular Plastics
- CAN/ULC S701-97 Type 2

PHYSICAL/CHEMICAL PROPERTIES

STYROFOAM CAVITYMATE SC insulation exhibits the properties and characteristics indicated in Tables 1 and 2 when tested as represented.

Prolonged exposure to ultraviolet radiation may cause the surface of STYROFOAM CAVITYMATE SC insulation to become yellow and dusty. A

U.S. PROPERTY CHART

TABLE 1

Physical Properties of STYROFOAM CAVITYMATE SC Insulation	
Property and Test Method	Value
Thermal Resistance ¹ per in., ASTM C518 @ 75°F mean temp., ft ² •h•°F/Btu min., R-value ²	5.0
Compressive Strength ³ , ASTM D1621, psi, min.	16
Water Absorption, ASTM C272, % by volume, max.	0.1
Water Vapor Permeance, ASTM E96, perms, max.	1.1
Maximum Use Temperature, °F	165
Coefficient of Linear Thermal Expansion, ASTM D696, in/in•°F	3.5 x 10 ⁻³

¹ Based on 1" thickness.

² R means resistance to heat flow. The higher the R-value, the greater the insulating power.

³ Vertical compressive strength at 10 percent deformation or at yield, whichever occurs first.

CANADA PROPERTY CHART

TABLE 2

Physical Properties of STYROFOAM CAVITYMATE SC Insulation	
Property and Test Method	Value
Thermal Resistance ¹ per in., ASTM C518 @ 75°F mean temp., ft ² •h•°F/Btu (m ² •°C/W) min., R-value (RSI) ²	5.0 (.88)
Compressive Strength, ASTM D1621, min., at 10% deflection or yield; whichever comes first, psi (kPa)	16 (110)
Water Absorption, ASTM D2842, % by volume, max.	0.9
Water Vapour Permeance, ASTM E96, perms, (ng/Pa•s•m ²), max.	1.5 (90)
Maximum Use Temperature, °F (°C)	165 (74)
Coefficient of Linear Thermal Expansion, ASTM D696, in/in•°F (mm/m•°C)	3.5 x 10 ⁻³ (6.3 x 10 ⁻²)

¹ Based on 1" (25.4 mm) thickness.

² R means resistance to heat flow. The higher the R-value or RSI, the greater the insulating power.

STYROFOAM CAVITYMATE SC Insulation

TABLE 3

light-colored, opaque protective covering should be used if excessive solar exposure is expected. The surface degradation will have no measurable effect on the insulating value of the plastic foam unless the deterioration is allowed to continue until actual foam thickness is lost. Since the dust would impair the performance of adhesives and finishes, the dusty surface should be brushed off before these products are applied.

For chemical resistance properties of STYROFOAM CAVITYMATE SC insulation see Table 3.

ENVIRONMENTAL DATA
STYROFOAM CAVITYMATE SC insulation is manufactured with HCFC blowing agents, which have 94 percent less ozone depletion potential than standard CFC blowing agents.

STYROFOAM CAVITYMATE SC insulation is reusable in many applications and can be recycled.

5 Installation

Boards of STYROFOAM CAVITYMATE SC insulation are easy to handle, cut and install.

Chemical Resistance of STYROFOAM CAVITYMATE SC Insulation			
Acid, inorganic	Good	Gases, carbon hydroxide (CH ₄)	Good
Acid, organic	Good	Gases, chlorofluorocarbons	Good
Alcohol	Good	Gases, dioxide (O ₂)	Good
Asphalts, water-based	Good	Gases, nitrous hydroxide (NH ₃)	Good
Bases (caustics)	Good	Gases, sulfur dioxide (SO ₂)	Good
Bleach	Good	Mineral oil USP	Excellent
Brines and other salts	Good	Paints, alcohol-based	Good
Cements and mortar	Good	Paints, water-based	Good
Gases, carbon dioxide (CO ₂)	Good	Water	Good

Contact a local Dow representative or access the literature library for more specific instructions

U.S.:
www.dowstyrofoam.com
/architect
Canada:
www.dowstyrofoam.ca
/4architects

6 Availability

STYROFOAM CAVITYMATE SC insulation is distributed through an extensive network. For product availability or for the name of your local Dow sales representative, call:

U.S.: 1-866-583-BLUE (2583)
Canada:
English – 1-866-583-BLUE (2583)
French – 1-800-565-1255

7 Warranty

Not applicable.

8 Maintenance

Not applicable.

9 Technical Services

Dow can provide technical information to help address questions about using STYROFOAM CAVITYMATE SC insulation. Technical personnel are available at Dow sales offices to assist with any insulation project. For product literature and technical information, please call our Customer Information Center.

U.S.: 1-866-583-BLUE (2583)
Canada:
English – 1-866-583-BLUE (2583)
French – 1-800-363-6210

10 Filing Systems

- U.S.:
www.dowstyrofoam.com
/architect
- Canada:
www.dowstyrofoam.ca
/4architects
- www.sweets.com

IN THE U.S.:

- For Technical Information: **1-866-583-BLUE (2583)**
- For Sales Information: **1-800-232-2436**

THE DOW CHEMICAL COMPANY

- Building & Construction • 200 Larkin • Midland, MI 48674
www.dowstyrofoam.com/architect

IN CANADA:

- For Technical Information (English): **1-866-583-BLUE (2583)**; (French): **1-800-363-6210**
- For Sales Information (English): **1-800-232-2436**; (French): **1-800-565-1255**

DOW CHEMICAL CANADA INC.

- Building & Construction • Suite 2200 • 250 - 6th Ave. SW • Calgary, AB T2P 3H7
www.dowstyrofoam.ca/4architects

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

COMBUSTIBLE: Protect from high heat sources. For more information, consult MSDS and/or call Dow at 1-866-583-BLUE (2583). In an emergency, call Dow (U.S.: 1-989-636-4400) (Canada: 1-519-339-3711). Local building codes may require a protective or thermal barrier. Contact your local building inspector for more information.

NOTE: Building and/or construction practices unrelated to insulation or housewrap could greatly affect moisture and the potential for mold formation. No material supplier, including Dow, can give assurance that mold will not develop in any specific system.

